

SPECIFICATION GUIDE – HALO GLASS

Features

By combining the principles of our core glass processes ‘veil’ and ‘formed’, we sculpt the glass surface by carving up to 3mm deep then kiln fire the glass to soften the shape and texture of its surface.

HALO’s jewel like appearance is a result of its dual translucencies, and its softened 3D form. Available in annealed glass, or laminated safety glass in custom sizes, HALO can also be supplied with bespoke printed interlayers, colour backed or even mirrored.

Manufacturer: Axolotl

Process: Halo

Glass type: Clear, Low Iron, Bronze, Grey, Green, Starfire

Treatment: Toughened, annealed, toughened laminated, annealed laminated, toughened/annealed laminated, heat strength.

Thickness: 10mm, 12mm, 15mm, 19mm, 25mm,

Panel sizes:

Quantity:

Pattern/Texture:

Effect: Mirror back, Matt Blast face 1 (MB1), Matt Blast face 2 (MB2), MB1 & MB2, Deep Carve face 1 (DC1), Deep Carve face 2 (DC2), DC1 + DC2, DC2 + paint, DC1 + MB2 100%, DC2 and MB1 100%, colour back, Shimmer back, laminate, translucent, soft white, pure white, clear.

Colour: Paint colour, laminate colour

Edge Type: Flat grind, belt arris, flat polish, water jet cut.

As an example for a Glass Halo sample you would write;

Manufacturer: Axolotl
Process: Halo
Glass Type: Low Iron
Treatment: Annealed laminated
Thickness: 10+10mm
Panel sizes: 1200 x 1800mm
Quantity: 30
Pattern: Custom Crab Apple
Effect: DC1
Colour: N/A
Edge Type: Flat polish
To approved artwork



Product **Halo Glass**
Glass Type **Low Iron**
Thickness **10 -21.52mm**
Treatment **Annealed / Laminated**
Design **Crabapple**
Effect **Halo1 + Mirror2**

6/73 Beauchamp Rd
Matraville 2036
NSW, Australia
ABN 98 000 377 686

+ 612 9666 1207
+ 612 9666 1210
info@axolotl.com.au
www.axolotl.com.au